POLYVANTIS

PRODUCT DATASHEET

LEXAN™ 8B35VE FILM

DESCRIPTION

LEXAN™ 8B35VE Film is a transparent polycarbonate film, velvet on one side and very fine matte on the other that offers excellent clarity, high heat resistance, and superior dimensional stability in all thicknesses. LEXAN 8B35VE Film can be printed using traditional solvent-based inks as well as IR and UV curing inks. It offers ease of processing for thermoforming, hydroforming, embossing, die cutting and bending.

TYPICAL PROPERTY VALUES*

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	8500	ISO 527	MPa	60
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2100
Tensile Elongation at Break	ASTM D882	%	>100	ISO 527	%	>100
Gardner Impact Strength at 0.03” (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8	ISO 34	kN/m	245
Propagation	ASTM D1922	g/mil	30-55	NA	kN/m	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010” (0.25 mm)	ASTM D2176-69	double folds	60			60
0.020” (0.50 mm)	ASTM D2176-69	double folds	20			20
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft^2/°F/in	1.35	DIN 52612	W/m°K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10^{-5}/°F)	3.2	ISO 11359	(x10^{-5}/°C)	7.0
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 / D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	302	ISO 306	°C	150
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75	°C	135
Shrinkage at 302°F (150°C)	ASTM D1204	%	0.80		%	<0.2
Brittleness Temperature	ASTM D746	°F	-210		°C	-135

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
PHYSICAL						
Density	ASTM D792	slug/ft^3	2.4	ISO 1183	kg/m^3	1230
Water Absorption, 24 hrs.	ASTM D570	%	0.35	ISO 62	%	0.35
Surface Roughness (RMS)	ASME B46-1	-	6.3(VFM)/34(M)	-	-	-
Surface Roughness (RA)	-	-	-	DIN4768	µm	0.5-1.5(VFM)) 2.6-5.2(V)
Surface Tension(1st surface/ 2nd surface)	Dyne Pens	Dyne	>34/>34	-	-	-
OPTICAL						
Refractive Index @77°F (25°C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	86			
Yellowness Index	ASTM D1925	%	1.9			
Haze	ASTM D1003	%	100			
Gloss over Flat Black min/max	ASTM D523-60	%	2.8-13.2(VFM)	ISO 2813	-	2.8-13.2(VFM)
@ 60°			2.0-9.8 (V)			2.0-9.8 (V)

- These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local POLYVANTIS representative or the POLYVANTIS Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.005 - 0.010" (0.125 - 0.250 mm)	± 8%
0.015-0.020" (0.375-0.500 mm)	± 5%

UL FLAMMABILITY RATING / PERFORMANCE LEVELS

THICKNESS	RATING
0.005-0.020" (0.125-0.500 mm)	UL94V-2
File Number E539152	

© POLYVANTIS PV_DS_001_8B35VE-FILM_ENG_08-24