POLYVANTIS

PRODUCT DATASHEET

LEXAN™ 8B36 FILM

DESCRIPTION

LEXAN™ 8B36 film is a one side suede, one side matte transparent polycarbonate film. It offers high temperature resistance, excellent dimensional stability, and good printability without pretreatment making it very suitable for multi-layer printing. The heavy suede texture offers mar resistance, and the product can be used over light-emitting devices. Its low gloss level reduces glare in automobile interiors and offices.

TYPICAL PROPERTY VALUES*

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2100
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100
Gardner Impact Strength at 0.03”	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propagation	ASTM D1922	g/mil	30-55		kN/m	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010” (0.25 mm)	ASTM D2176-69	double folds	60			
0.020” (0.50 mm)	ASTM D2176-69	double folds	20			
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft^2/°F/i	1.35		W/m°K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10^{-5}/°F)	3.2	ISO 11359	(x10^{-5}/°C)	7
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 /	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	323		°C	150
Heat Deflection Temp. by TMA at1.8		°F	290	ISO 75	°C	135
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
PHYSICAL						
Density	ASTM D792	slug/ft^3	2.3	ISO 1183	kg/m^3	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Energy (1st/2nd surface)	Dyne Pens	Dyne	38/32			
Surface Tension (1st/2nd surface)	ASTM D3363	-	>44/>44			
OPTICAL						
Refractive Index @77˚F (25˚C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	85			
Yellowness Index	ASTM D1925	%	2			
Haze	ASTM D1003	%	102			
Gloss over Flat Black min/max @ 60˚	ASTM D523-	-	4	ISO 2813	-	4

*These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local POLYVANTIS representative or the POLYVANTIS Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.010-0.015" (0.250-0.375 mm)	± 5%
0.020" (0.500 mm)	± 3%

POLYVANTIS

Polycarbonate products are sold globally under the trademark LEXAN™ Film & Sheet, owned by SABIC or its subsidiaries or affiliates.

polyvantis.com

LEXAN™ POLYCARBONATE FILM & SHEET Tough, Virtually Unbreakable

LEXAN is a trademark of SABIC

© POLYVANTIS PV_DS_8B36-FILM_ENG_10-25