POLYVANTIS

PRODUCT DATASHEET

LEXAN™ SGC10XX SHEET

DESCRIPTION

LEXAN™ SGC10xx Solar Grade Coextruded sheet for signs combines the impact strength of LEXAN polycarbonate sheet with a proprietary UV-resistant cap layer that provides long-term protection against weathering. LEXAN SGC10xx sheet are backed by ten-year limited written warranty against yellowing, loss of light transmission and breakage. Providing long-lasting clarity over a wide range of environments, LEXAN SGC10xx sheet offers extended service life and reduced life-cycle material costs. It is an excellent candidate for all types of thermoformed or flat signs, whether screen-printed, painted or decorated with vinyl graphics.

TYPICAL PROPERTY VALUES*

PROPERTY	TEST METHOD	UNITS	VALUE
Physical			
Specific gravity	ASTM D792	-	1.20
Light Transmission @ .118" thickness	ASTM D1003	%	87
Rockwell Hardness	ASTM D785	-	M70,R118
Mechanical			
Tensile Strength	ASTM D638	psi	
Ultimate			9,500
Tensile Modulus	ASTM D638	psi	285,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	340,000
Compressive Strength	ASTM D695	psi	12,500
Izod Impact Strength, up to 125 mils	ASTM D256A	ft-lbs/in	
Notched			12-16
Drop Ball Impact Strength, 1" dia.dart @ .236 thickness	POLYVANTIS Test ##	ft-lbs	
@ 73°F			>200
@ 0°F			>200
Thermal			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75×10^{-5}
Heat Deflection Temperature	ASTM D648	°F	
@ 264 psi			260
@ 66 psi			280

♦ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local POLYVANTIS Innovative Plastics, Specialty Film & Sheet representative.


See actual Product Warranty for conditions that may apply.

Measured by dropping a 25-pound dart (1" dia. tip) from a height of 8 feet.

UL FILE NUMBER: E539257


UV RESISTANCE

LEXAN™ SGC10xx sheet was exposed to accelerated QUV weathering. After exposure comparable to 10 years in South Florida.



IMPACT RESISTANCE

LEXAN™ SGC10xx and SG5xxx sheet has up to 30 times the impact strength of “Acrylic” and 10 times the impact strength of “Modified Acrylic".



POLYVANTIS

Polycarbonate products are sold globally under the trademark LEXAN™ Film & Sheet, owned by SABIC or its subsidiaries or affiliates.

polyvantis.com

LEXAN™ POLYCARBONATE FILM & SHEET Tough, Virtually Unbreakable

LEXAN is a trademark of SABIC

© POLYVANTIS PV_DS_SGC10XX_SOS_ENG_06-24